
Self adhesive tapes — Determination of peel adhesion properties

*Rubans auto-adhésifs — Détermination des caractéristiques du
pouvoir adhésif linéaire*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 29862:2018](https://standards.iteh.ai/catalog/standards/sist/12f01eb4-42f0-4f7c-b9da-21f130c2bffb/iso-29862-2018)

[https://standards.iteh.ai/catalog/standards/sist/12f01eb4-42f0-4f7c-b9da-
21f130c2bffb/iso-29862-2018](https://standards.iteh.ai/catalog/standards/sist/12f01eb4-42f0-4f7c-b9da-21f130c2bffb/iso-29862-2018)



iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 29862:2018

<https://standards.iteh.ai/catalog/standards/sist/12f01eb4-42f0-4f7c-b9da-21f130c2bffb/iso-29862-2018>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2018

All rights reserved. Unless otherwise specified, or required in the context of its implementation, no part of this publication may be reproduced or utilized otherwise in any form or by any means, electronic or mechanical, including photocopying, or posting on the internet or an intranet, without prior written permission. Permission can be requested from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
CP 401 • Ch. de Blandonnet 8
CH-1214 Vernier, Geneva
Phone: +41 22 749 01 11
Fax: +41 22 749 09 47
Email: copyright@iso.org
Website: www.iso.org

Published in Switzerland

Contents

	Page
Foreword	v
1 Scope	1
2 Normative references	2
3 Terms and definitions	2
4 Significance and use	2
5 Method 1 — Self adhesive tapes — Measurement of peel adhesion from stainless steel at an angle of 180°	3
5.1 Principle	3
5.2 Materials	3
5.3 Apparatus	3
5.4 Test samples and test pieces	4
5.5 Procedure	5
5.5.1 Standard test conditions	5
5.5.2 Preparation of the panel	5
5.5.3 Peel adhesion	5
5.6 Expression of results	5
5.7 Test report	5
6 Method 2 — Self adhesive tapes — Measurement of peel adhesion from its own backing at an angle of 180°	6
6.1 Principle	6
6.2 Apparatus	6
6.3 Test samples and test pieces	6
6.4 Procedure	7
6.4.1 Standard test conditions	7
6.4.2 Preparation of the panel	7
6.5 Expression of results	7
6.6 Test report	7
7 Method 3 — Self adhesive tapes — Measurement of peel adhesion of double sided and transfer tapes at an angle of 180°	7
7.1 Principle	7
7.2 Materials	7
7.3 Apparatus	7
7.4 Test samples and test pieces	7
7.5 Procedure	8
7.5.1 Standard test conditions	8
7.5.2 Preparation of the panel	8
7.5.3 Procedure for open side of double sided or adhesive transfer tape	8
7.5.4 Procedure for closed side of double sided or adhesive transfer tape	8
7.6 Expression of results	8
7.7 Test report	8
8 Method 4 — Self adhesive tapes — Measurement of adhesion of the liner to an adhesive tape at an angle of 180°	9
8.1 Principle	9
8.1.1 Double sided adhesive tapes	9
8.1.2 Single sided adhesive tapes	9
8.2 Materials	9
8.3 Apparatus	9
8.4 Test samples and test pieces	9
8.5 Procedure	9
8.5.1 Double sided tapes	9
8.5.2 Single sided tape	9
8.6 Expression of results	10

8.7 Test report.....	10
Annex A (normative) Self adhesive tapes — Measurement of peel adhesion from a surface at low temperature.....	11
Annex B (normative) Self adhesive tapes — Measurement of peel adhesion from a surface at an angle of 90°.....	12
Bibliography.....	14

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 29862:2018](https://standards.iteh.ai/catalog/standards/sist/12f01eb4-42f0-4f7c-b9da-21f130c2b1b/iso-29862-2018)

<https://standards.iteh.ai/catalog/standards/sist/12f01eb4-42f0-4f7c-b9da-21f130c2b1b/iso-29862-2018>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The procedures used to develop this document and those intended for its further maintenance are described in the ISO/IEC Directives, Part 1. In particular the different approval criteria needed for the different types of ISO documents should be noted. This document was drafted in accordance with the editorial rules of the ISO/IEC Directives, Part 2 (see www.iso.org/directives).

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights. Details of any patent rights identified during the development of the document will be in the Introduction and/or on the ISO list of patent declarations received (see www.iso.org/patents).

Any trade name used in this document is information given for the convenience of users and does not constitute an endorsement.

For an explanation on the voluntary nature of standards, the meaning of ISO specific terms and expressions related to conformity assessment, as well as information about ISO's adherence to the World Trade Organization (WTO) principles in the Technical Barriers to Trade (TBT) see the following URL: www.iso.org/iso/foreword.html.

This document was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*.

This second edition cancels and replaces the first edition (ISO 29862:2007) of which it constitutes a minor revision.

The changes compared to the previous edition are as follows:

- the normative references in [Clause 2](#) have been updated;
- definitions have been added in [Clause 3](#) for “self adhesive tape”, “liner” and “double sided adhesive tape”;
- a Bibliography has been added;
- the text has been editorially revised to comply with the most recent editing rules.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 29862:2018

<https://standards.iteh.ai/catalog/standards/sist/12f01eb4-42f0-4f7c-b9da-21f130c2bffb/iso-29862-2018>

Self adhesive tapes — Determination of peel adhesion properties

1 Scope

This document specifies a series of methods for the determination of peel adhesion properties of self adhesives tapes.

This document contains:

- Method 1: Self adhesive tapes – Measurement of peel adhesion from stainless steel at an angle of 180°;
- Method 2: Self adhesive tapes – Measurement of peel adhesion from its own backing at an angle of 180°;
- Method 3: Self adhesive tapes – Measurement of peel adhesion of double sided and transfer tapes at an angle 180°;
- Method 4: Self adhesive tapes – Measurement of adhesion of the liner to an adhesive tape at an angle of 180°.

[Annexes A](#) and [B](#) specify further variations in the testing protocol according to specific conditions.

A guide to the use of these methods is given in [Table 1](#).

Table 1 — Methods and annexes

Method	Angle of peel	Temperature of test	
		23 °C	Low temperature
Method 1 Adhesion to steel	180°	—	Annex A
	90°	Annex B	-
Method 2 Adhesion to back- ing	180°	—	Annex A
	90°	Annex B	—
Method 3 Adhesion of double sided and transfer tape	180°	—	Annex A
	90°	Annex B	—
Method 4 Adhesion of liner	180°	—	Annex A
	90°	Annex B	-

NOTE 1 These methods provide a means of assessing the uniformity of the adhesion of a given type of self adhesive tape. The assessment may be within a roll of tape, between rolls or between production lots.

NOTE 2 Variations in the tape backing and adhesive affect the response. Therefore these methods cannot be used to pinpoint the specific cause(s) of non uniformity.

NOTE 3 These test methods may not be appropriate to test tapes having either relatively stiff backings, stiff liners or backing showing high stretch at low forces. These characteristics will result in a high variability for the test response which is not a true indication of the real nature of the adhesive bond.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12481, *Self adhesive tapes — Terminology*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 12481 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <https://www.iso.org/obp>

3.1

peel adhesion

force required to peel a strip of adhesive tape from a specified substrate at a specified angle and speed

3.2

open side

<adhesive> surface of the adhesive on a double sided tape which is exposed on normal unwinding or separation of the first liner

3.3

closed side

<adhesive> surface of the adhesive on a double sided tape which normally remains in contact with the release liner on normal unwinding or separation of the first liner

3.4

transfer tape

adhesive tape having two available pressure sensitive surfaces without the need for a carrier and with a release liner separating the adhesive surfaces. The adhesive may contain reinforcing material

3.5

self adhesive tape

pressure sensitive adhesive

adhesive which in a dry state is permanently tacky at room temperature and adheres readily to surfaces under brief and light pressure

3.6

liner

treated sheet to cover the adhesive temporarily to facilitate handling or unrolling

3.7

double sided adhesive tape

tape where adhesive is applied to both sides of the carrier

4 Significance and use

These test methods are tools for quality control use. Given specific self adhesive tape and a requirement in terms of the minimum or maximum value expected for this tape, the data from the test can be used in conjunction with acceptance criteria.

Test methods 1, 2, 3, and [Annexes A](#) and [B](#) can show the relative bond strength of a given tape to one or more surfaces (material and texture) as compared to the standard stainless steel panel. Substitution of representative samples of materials in question for the standard steel panel would suffice to do this.

Test methods 1, 2, 3, and [Annexes A](#) and [B](#) cannot be used to compare two self adhesive tapes of the same type but of different manufacture for their ability to adhere to a surface. This is because the measured peel force is not normalised for a fixed area of stress. The area under stress varies with backing stiffness and adhesive rheology (firmness). Two different tapes seldom agree in these properties.

Test method 4 can show the amount of force required to remove a liner that covers the adhesive side of a tape at a specified peel rate. The force will be different at other peel rates.

These test methods may not provide design information as there is usually no direct relationship between peel adhesion and any functional requirement.

5 Method 1 — Self adhesive tapes — Measurement of peel adhesion from stainless steel at an angle of 180°

5.1 Principle

The method 1 gives a measure of the force required to remove at an angle of 180° an adhesive tape which has been applied to a stainless steel panel.

A length of adhesive tape is applied to a standard plate which is then fixed vertically in one clamp of a tensile testing machine. The other clamp of the machine pulls the free end of the adhesive tape at an angle of 180° to the plate.

The adhesive strength is measured by the force required to peel the adhesive tape continuously from the plate, the line of separation being perpendicular to the direction of the applied force.

5.2 Materials

5.2.1 Absorbent cleaning material, surgical gauze, cotton wool or tissue. To be suitable, materials shall be lint free during use, absorbent, contain no additives that are soluble in the solvents listed in [5.2.2](#) and made exclusively from virgin materials.

5.2.2 One or more of the following solvents:

- diacetone alcohol non-residual grade (4-hydroxy-4-methyl-2-pentanone);
- methanol;
- methyl ethyl ketone;
- acetone;
- *n*-heptane;
- a mixture of *n*-heptane and a fluorinated hydrocarbon such as refrigerant (suitable when toxicity or flammability restrictions apply).

Solvents shall be of general purpose chemical grade and held in a suitable dispensing system.

5.3 Apparatus

5.3.1 Test piece cutter

An appropriate test piece cutter shall hold two single edge razor blades in parallel planes a precise distance apart, to form a cutter of exact specimen width; two cutters, 12 mm and 24 mm cutting width, shall be available or appropriate alternatives which will not cause edge damage. The precision of the razor blade separation shall be the nominal width $\pm 0,1$ mm.

5.3.2 Tensile testing machine

A constant rate of extension (CRE) tension tester shall be used. It is proposed to use an electronic machine taking at least one reading per mm of tape peeled. The tester shall have two clamps with centres in the same plane, parallel with the direction of the motion on the same plane, parallel with the direction of the motion on the stressing clamp and so aligned that they will hold the specimen wholly in the same plane; a means of moving the stressing clamp at a uniform rate of $(5 \pm 0,2)$ mm/s and a device for recording load. The instrument shall be calibrated such that a maximum error of 2 % is allowed on the reading.

5.3.3 Stainless steel panels

These shall be perfectly flat, at least 125 mm long and 50 mm wide and at least 1,1 mm thick, stainless steel type 1.4301 in accordance with the 2 R quality defined in EN 10088-2, having a bright annealed finish with a surface roughness of $50 \text{ nm} \pm 25 \text{ nm}$. Panels showing stains, discoloration or many scratches are not acceptable. New panels shall be cleaned prior to use as described in 5.5.2 except with ten washes of the final solvent. Between uses the panel test surface shall be protected from scratches and contamination and the panels shall be stored in the conditions described in 5.4.1.

5.3.4 Roller mechanically or hand operated

5.3.4.1 A steel roller $(85 \pm 2,5)$ mm in diameter and $(45 \pm 1,5)$ mm in width, covered with rubber approximately 6 mm in thickness, having a hardness of (80 ± 5) Shore A. The surface shall be a true cylinder, void of any convex or concave deviations. The mass of the roller shall be $(2 \pm 0,1)$ kg.

5.3.4.2 No part of the apparatus shall increase the mass of the roller during use. The roller shall move either mechanically or by hand at the rate of $(10 \pm 0,5)$ mm/s.

5.4 Test samples and test pieces

5.4.1 Condition the sample rolls of tape in the standard conditions of (23 ± 1) °C and (50 ± 5) % relative humidity (RH). Test at these conditions unless otherwise specified [see 5.7 i)]. If these tolerances cannot be maintained, the closest possible tolerances shall be used and these revised tolerances quoted in the report.

5.4.2 The test piece shall be 24 mm wide. A limit deviation of $\pm 0,5$ mm shall be allowed. The length shall be approximately 300 mm.

Where the width of the specimen is less than 24 mm, apply one or more additional strips of the tape to give an equivalent width of 24 mm for rolling purposes. Alternatively acceptable rolling pressure may be obtained with a 1 kg roller on samples with width 8,5 mm to 17 mm or with 2 kg roller on samples with widths greater than 17 mm to a maximum of 34 mm.

5.4.3 Discard at least three but no more than six outer wraps of tape from the sample roll before taking the test pieces for testing.

5.4.4 Remove one test piece for each test to be performed. Remove the test piece from a freely rotating roll at the rate of 500 mm/s to 750 mm/s. Where high unwind force makes it impossible to remove the test piece at the prescribed rate, remove it at a rate as close to 500 mm/s as possible.

5.4.5 When the tape is wider than 24 mm, test pieces of the widest specified width are to be cut with an apparatus as described in 5.3.1 from the centre of a strip removed from the roll in accordance with 5.4.4.

5.4.6 Apply the test pieces within 5 min after unwinding.

5.5 Procedure

5.5.1 Standard test conditions

Standard test conditions shall be the same as [5.4.1](#) for test pieces and test samples conditioning.

5.5.2 Preparation of the panel

Dispense one of the solvents listed in [5.2.2](#) on to the panel, wiping it to dryness with fresh absorbent cleaning material. Repeat for a total of three washes with this solvent.

Final wipe shall be with methyl ethyl ketone or acetone. The panel should be allowed to dry for at least 10 min. Panels not used within 10 h should be recleaned.

In order to obtain consistent results a new panel shall be wiped at least 10 times with final solvent before use.

Discard plates showing stains, discoloration, or many scratches. Avoid contacting panel surface with fingers. During storage panel should, be protected from damage or contamination.

5.5.3 Peel adhesion

5.5.3.1 Remove a 300 mm test piece of the tape to be tested, as described in [5.4.4](#). Fold 12 mm at one end, adhesive to adhesive to form a tab. Touch the other end of the test piece to an end of the test panel. Holding the tab end of the test piece so that it does not make contact with the panel but is positioned loosely above it, roll mechanically or by hand twice in each lengthwise direction, causing the roller to apply the tape to the panel. This prevents entrapment of air between the adhesive and the panel. Should this occur, discard the test piece.

Individually prepare each test piece and test within 1 min.

NOTE Longer dwell time will give different results. Peel adhesion increases with dwell time at different rates for various tapes. A longer dwell time can be chosen purposely.

5.5.3.2 Stripping the test piece. Double back the folded end of the tape at an angle of 180° and peel 25 mm of the tape from the panel. Clamp that end of the panel into one of the jaws of the tensile testing machine and the tape into the other jaw. Operate the tester at $(5,0 \pm 0,2)$ mm/s.

After the movable jaw is started in motion disregard the values obtained while the first 25 mm of tape is mechanically peeled. Use the average force obtained during peeling of the next 50 mm of adhesive tape from the panel as the adhesion value.

The tester should know that by prolonged handling, heat is transmitted to the stainless steel test panel. Therefore during and after application of the adhesive tape to the test panel, the panel should be handled as little as possible.

5.6 Expression of results

Express the peel adhesion in newtons per 10 mm, if necessary first converting the observed force in newtons.

5.7 Test report

The test report shall include the following information:

- a) a reference to this document;
- b) statement that this test method was used and indicating any deviations from the method as written;